

QUALITY CERTIFICATE

№ 2601-034 Issued Date: 10.01.2026

Manufacturer: PlasmaTec LLC
18 Pravednykiv svitu str., Vinnytsia, Vinnytsia
region, Vinnytsia district, Ukraine, 21036

| Product |
|---|
| Welding electrodes Monolith 7018-1 H4R TM MONOLITH d 3.2 mm (1/8"): vacuum 2 kg (4.4 LB) |

| | |
|---|--|
| Specification/Classification | AWS A5.1 / SFA-5.1: E7018-1 H4R EN ISO 2560-A- E 46 5 B 3 2 H5 CSA W48: E4918-1 H4 4Y46H5 |
| Batch classification according to EN ISO 14344 | C5 |
| Lot Number | 003 |

Mechanical properties of weld metal EN 10204, type 2.2

| Index | Requirements (AWS A5.1) | Typical data |
|--|-------------------------|--------------|
| Tensile strength, (MPa/ksi) | min. 490 (70) | 579 (84) |
| Elongation, % | min. 22 | 28 |
| Yield strength, (MPa/ksi) | min. 400 (58) | 497 (72) |
| Impact energy (KV), J/(ft-lb) (-50°C/-58°F) | min. 27 (20) | 87 (64) |
| Diffusible hydrogen, ml/100g | max. 4 | 3.2 |


Chemical analysis of weld metal, % EN 10204, type 3.1

| Index | Requirements (AWS A5.1) | Actual data |
|----------------------|-------------------------|-------------|
| C | max. 0.15 | 0.09 |
| Si | max. 0.75 | 0.6 |
| Mn | max. 1.6 | 1.28 |
| P | max. 0.035 | 0.026 |
| S | max. 0.035 | 0.009 |
| Cr | max. 0.2 | 0.08 |
| Ni | max. 0.3 | 0.03 |
| Mo | max. 0.3 | 0.004 |
| V | max. 0.08 | 0.01 |
| Mn+Cr+Ni+Mo+V | max. 1.75 | 1.404 |

Post weld heat treatment - As welded

The product was manufactured and supplied according to a Quality System Program that meets the requirements of ISO 9001. The delivery conditions are in accordance with EN ISO 544.

Head of Technical Control: Andrii Babyn



quality@plasmatec.com.ua, +380(67)433-19-36 (Viber, WhatsApp, Telegram)

Lot Number identification: **001 3.2 XO** (example of Lot number), where **001** - actual Lot Number, 3.2 XO - additional information (3.2 - electrode size in mm; X - pressing team, O - packing team)